






Technical Specification		Commodore 800	Commodore 1000	Emperor 1000	Emperor 1200	Emperor 1450
	Test					
Manufacturing Technique		1/10 Printed Saxony	1/10 Printed Saxony	1/10 Printed Saxony	1/10 Printed Saxony	1/10 Printed Saxony
Pile Composition		100% PA 6,0 Crealon	100% PA 6,0 Crealon	100% PA 6,6 Invista	100% PA 6,6 Invista	100% PA 6,6 Invista
						
Secondary Backing		Weaveback	Weaveback	Weaveback	Weaveback	Weaveback
Width		400 cm	400 cm	400 cm	400 cm	400 cm
Roll Length		25 m	25 m	25 m	25 m	25 m
Pile Height		7 mm	7,5 mm	6,5 mm	7,5 mm	9 mm
Pile Weight		800 g / m ²	1000 g / m ²	1050 g / m ²	1200 g / m ²	1450 g / m ²
Total Height		9 mm	9,5 mm	8,5 mm	9,5 mm	11 mm
Total Weight		1650 g / m ²	1900 g / m ²	1850 g / m ²	2100 g / m ²	2400 g / m ²
Number of Tufts		185 040 / m ²	201 500 / m ²	192 915 / m ²	206 695 / m ²	212 600 / m ²
Minimum Order Quantity		500 m ² / colorbank	500 m ² / colorbank	500 m ² / colorbank	500 m ² / colorbank	500 m ² / colorbank
Fastness to Rubbing (Dry)	ISO 105 X-12	4-5	4-5	4-5	4	4
Fastness to Rubbing (Wet)	ISO 105 X-12	5	4-5	4	4-5	4-5
Water Fastness	ISO 105 E-01	4-5	4-5	4-5	4-5	4-5
Fastness to Light	ISO 105 B-2	5	6	6-7	6-7	6-7
Thermal Resistance	ISO 8302	0,072 m ² K/ W	0,0813 m ² K/ W	0,061 m ² K/ W	0,067 m ² K/ W	0,07 m ² K/ W
Impact Sound Insulation	ISO 140 - 8	25 dB	31 dB	28 dB	30 dB	37 dB
		